

Jok 201095



①2

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau


INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B23K 26/00, 33/00		A1	(11) International Publication Number: WO 99/08829
			(43) International Publication Date: 25 February 1999 (25.02.99)
(21) International Application Number: PCT/CA98/00779 (22) International Filing Date: 14 August 1998 (14.08.98) (30) Priority Data: 2,209,804 15 August 1997 (15.08.97) CA (71) Applicant (for all designated States except US): POWER-LASERS LTD. [CA/CA]; Advanced Technology Centre, Units 2 & 3, 543 Mill Street, Kitchener, Ontario N2G 2Y5 (CA). (72) Inventor; and (75) Inventor/Applicant (for US only): GU, Hongping [CN/CA]; Apartment 127, 155 University Avenue West, Waterloo, Ontario N2L 3E5 (CA). (74) Agents: ORANGE, John, R., S. et al.; Orange & Associates, Toronto Dominion Bank Tower, Suite 3600, Toronto-Dominion Centre, P.O. Box 190, Toronto, Ontario M5K 1H6 (CA).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.	

(54) Title: METHOD OF LASER BEAM WELDING OF ZINC-COATED STEEL SHEET

(57) Abstract

A pair of coated components are laser welded to one another by initially forming protuberances on one of the components. The protuberances maintain juxtaposed surfaces separated and the components are then laser welded to one another. The separation of the surfaces vents vapor generated by the coating.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

METHOD OF LASER BEAM WELDING OF ZINC-COATED STEEL SHEET

The present invention relates to a method of making lap joint of zinc coated steel
5 sheets with a laser beam.

BACKGROUND OF THE INVENTION

The increased use of zinc-rich coated steel sheets in auto-body components for
enhanced corrosion resistance poses a demand for an acceptable welding method to join these
10 kinds of sheets. Laser beam welding has an advantage of low total heat input and thus causes
a low distortion to the zinc-rich coating on the sheet. Therefore laser beam welding is being
evaluated as a desirable joining technique for such sheet steel in butt and lap joint
configurations. However, a problem arises with welding these materials in the lap-joint
configuration due to the low boiling point of zinc (906°C) compared with the melting
15 temperature of steel (~1550°C).

If there is no joint clearance between the sheets the zinc vapor during welding can
only escape through the molten welding pool, and this typically results in excessive weld
porosity or complete expulsion of the weld metal. In order to make a good quality weld, there
are, in principle, two solutions to get around this problem: (1) creating a zinc-vapor venting
20 channel during welding; or (2) removing the zinc coating in the welding pass. Both of these
approaches need additional techniques to be realized. Many techniques have been developed
to provide a gap between sheets to perform laser welding and to remove the zinc coat at the
welding spot. These approaches typically require the use of supplementary components or
spacers and cannot be employed in the production line, since additional equipment is required
25 to create a gap or remove the coating. This will incur a significant expense and increase
production time.

It is therefore an object of the present invention to obviate or mitigate the above disadvantages.

SUMMARY OF THE INVENTION

5 The present invention is intended to provide a practical and flexible way of making laser beam lap weld of zinc coated steel sheets. In general terms, a laser beam interaction with one surface of the material is used to create an acceptable gap between the sheets before the welding pass is performed.

10 More specifically, protuberances are formed on one surface of one sheet by impingement of a laser beam which maintains opposed surfaces of the sheets in spaced relationship. In this manner, the welding may be completed entirely on a single welding apparatus in an efficient cost-effective manner. With such a technique, it is possible to make a curved welding pass and it is applicable to 3D welding configuration. Therefore, this technique makes the production of laser beam lap welds of the zinc coated steel sheets
15 possible using an existing butt welding system.

 The preferred embodiment of the invention relates to a method of creating a gap for vapor gas venting by the laser beam before welding is performed. The principle is that a laser beam pulse with an appropriate pulse length can melt a spot on the metal sheet when it interacts with the metal and solidification of the molten metal forms a protuberance. The
20 protuberance height above the sheet surface may be a few tenths millimeters. A series of protuberances in a line or curve serves as a spacer. When the laser pulse pre-processed sheet is put together with another sheet, a gap is formed. Laser welding can thus be performed along the spotted line/curve and go over the protuberances. The appropriate distance between two laser created protuberances depends upon the clamping force, laser beam power, scanning
25 speed and the thickness of the metal sheets. In lap welding, the sheet on which laser pulses

generate protuberances can be either the top one or the bottom one. For both configurations, good quality welds can be produced.

DESCRIPTION OF THE INVENTION

5 Embodiments of the invention will now be described by way of example only with reference to the accompanying drawings, in which

Figure 1 is a plan view of a pair of lap welded components;

Figure 2 is a view on the line 2-2 of the sequential steps in performing a weld on the components;

10 Figure 3 is an alternative embodiment showing the production of a spot weld;

Figure 4 is a photographic representation of a portion of one of the sheets shown in Figure 2;

Figure 5a is a photographic representation of a section on the weld shown in Figure 1;

15 Figure 5b is a photographic representation of a plan view of the weld shown in Figure 1; and

Figure 6 is photographic representations of welded components produced by the technique shown in Figure 2.

Referring therefore to Figure 1, a pair of components 10, 12 are connected by seam welding along a seam line 13 indicated in chain dot line. Each of the components is a steel
20 sheet having oppositely directed surfaces 16, 17 and 18, 20 respectively. Each of the surfaces has a rust inhibiting coating, typically a zinc coating 22 to provide protection from corrosion.

As shown in Figure 2, one of the components to be welded, namely zinc-coated steel sheet 10 is placed on a welding table (any kind of table used for laser welding). A series of laser beam pulses 14 transmitted through laser head 23 are used to impinge on one of the surfaces 16 of the sheet 10 to create a series of protuberances 15 along the intended weld line 13. This process can be done by moving laser beam 14 over the sheet 10 or by manipulating the focusing optics of the laser head.

Once the pulsed protuberances are formed, the zinc-coated steel sheet 12 is placed on top of the laser-pulsed sheet 10 so that surface 18 overlies the surface 16. Alternatively, of course, the laser-pulsed steel sheet 10 may be placed on top of the other zinc-coated steel sheet 12. Under either condition, the steel sheets 10, 12 are pressed together by a clamp (not shown). As a result, two sheets to be welded are held together and are ready to be welded.

The protuberances 15 form an air gap 24 between the opposed surfaces 16, 18 of overlapping portions of the zinc-coated steel sheets 10, 12 along the weld line 13.

The welding operation is carried out by applying laser beam 14 to the steel sheets 10, 12 as indicated in Figure 2 by arrow A. During the welding, the zinc vapor 26 of the zinc-coating 22 can flow into the air gap 24 surrounding the welding keyhole. Therefore, no air holes or very few air holes are formed in the solidified metal weld 19. Thus, the resultant weld is satisfactory in quality.

In a typical welding operation using a 1.5 kW CO₂ laser, the protuberances 15 were formed by beam pulses of 100 - 150 millisc in duration. The thickness of the sheet 10 was ~1.0 mm and the material galvanneal steel. The height of the protuberances 15 was in the order of 0.4 mm with a diameter of in the order of 2 mm. As can be seen from Figure 4, the protuberance is irregular but of sufficient height to maintain the surfaces 16, 18 separated. The spacing of the protuberances was about 50 mm for the material selected although this spacing may vary according to the material.

The components 10, 12 were seam welded using the 1.5 kW laser in continuous mode traveling at a welding speed of 1.5 in/sec. The resultant weld is shown in Figure 5 where it can be seen that good homogeneity has been obtained.

The above embodiment has been described with respect to seam welding but a similar
5 technique may be used for spot welding.

As shown in Figure 3, one of the components 10 to be welded is placed on a working table or frame. At the locations where laser spot welds are to be made, a laser beam pulse 14 impinges on surface 16 to create a protuberance 15. After all the locations are pulsed by laser beam 14, zinc-coated steel sheet 12 is placed on top and clamped. As a result of this
10 configuration, an air gap is formed between two zinc-coated steel sheets around the laser-generated humps. The welding operation is carried out by applying a laser beam 14 to the steel sheets adjacent to each protuberance 15. The laser beam draws a circle of small radius around the protuberance to provide a localized circular weld. Welding will not be affected if the path of the beam intercepts the protuberance.

15 As described in the seam welding embodiment above, the zinc vapor 26 escapes into the air gap around the hump. Therefore, a circular weld 19 is made and the resultant weld is satisfactory in quality. This circular weld can be considered as a spot weld.

It will be seen from the above description that the creation of natural spacer by this technique is simple and flexible as the laser beam can be put on anywhere on the sheet to
20 create protuberances and to perform welding. Moreover, implementation of lap welding can be done with present laser welding systems with little additional costs.

**THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE
PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:**

1. A method of laser welding a pair of juxtaposed components comprising the steps of
5 forming on one surface of one component a protuberance to project above said surface,
juxtaposing said components such that opposed surfaces are maintained separated by said
protuberance, and laser welding said components by impingement of a laser beam in the
region in which said surfaces are separated.
- 10 2. A method according to claim 1 wherein said protuberance is formed by impingement
by laser beam.
3. A method according to claim 1 wherein said weld is formed by rotating said beam
about one of said protuberance.
- 15 4. A method according to any preceding claim 1 in which a plurality to protuberances are
formed in spaced relationship along a surface of said one component.
5. A method according to claim 4 wherein said components are welded to one another by
20 translating said laser beam along said surface in the direction of said protuberances.
6. A method according to claim 4 wherein said components are welded to one another by
rotation of said beam about respective ones of said protuberances to provide a
generally circular weld.

25

7. A method according to any preceding claim wherein at least one of said components is coated with a rust inhibiting coating.

8. A method according to claim 7 wherein said coating includes zinc.

5

9. A method of welding a pair of sheet metal components having a corrosive resistant coating to one another comprising the steps of impinging a laser beam upon one surface of one of the components to form a plurality of localized protuberances thereon at spaced intervals, juxtaposing said sheets with said protuberances interposed between said sheets to maintain a separation thereof, and welding said sheets to one another by impingement of said beam in the vicinity of said protuberances.

10

10. A method according to claim 9 wherein said welding is performed by translating said beam across said components.

15

11. A method according to claim 10 wherein said beam is rotated about said protuberances to provide a circular weld.

12. A method according to claim 9 wherein said beam intersects said protuberances during welding.

20

1/6




Fig. 1

SUBSTITUTE SHEET (RULE 26)




Fig. 2




Fig. 3



Figure 4

SUBSTITUTE SHEET (RULE 26)

5/6





Figure 5

SUBSTITUTE SHEET (RULE 26)

INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 98/00779

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B23K26/00 B23K33/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B23K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	US 5 104 032 A (SPIES BERARD ET AL) 14 April 1992 see the whole document ---	1,4,5,7, 8 9,10
X A	FR 2 731 373 A (PEUGEOT) 13 September 1996 see the whole document ---	1,4,7,8 9
X A	US 5 454 480 A (MORRIS JR H EDWARD) 3 October 1995 see the whole document ---	1,4,7,8 9
X A	US 5 626 776 A (MORRIS JR H EDWARD) 6 May 1997 see the whole document ---	1,4,7,8 9
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

7 December 1998

Date of mailing of the international search report

17/12/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Aran, D

INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 98/00779

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 010, no. 130 (M-478), 14 May 1986 & JP 60 255294 A (KUBOTA TEKKO KK; OTHERS: 01), 16 December 1985	1,7,8
A	see abstract ----	9
X	DE 38 12 448 C (BAYERISCHEN MOTORENWERKE AG) 15 June 1989	1,7,8
A	see the whole document ----	9,10,12
A	US 5 389 761 A (KRESSE JR ALFRED L) 14 February 1995 see the whole document -----	1,9

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/CA 98/00779

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5104032	A	14-04-1992	DE 3933408 A	30-08-1990
			EP 0421091 A	10-04-1991
			ES 2048374 T	16-03-1994
			JP 2571976 B	16-01-1997
			JP 3193285 A	23-08-1991
FR 2731373	A	13-09-1996	NONE	
US 5454480	A	03-10-1995	US 5626776 A	06-05-1997
US 5626776	A	06-05-1997	US 5454480 A	03-10-1995
DE 3812448	C	15-06-1989	EP 0337182 A	18-10-1989
US 5389761	A	14-02-1995	DE 4432912 A	30-03-1995



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ :
B23K 26/00, 33/00

A1

(11) International Publication Number: WO 99/08829

(43) International Publication Date: 25 February 1999 (25.02.99)

(21) International Application Number: PCT/CA98/00779

(22) International Filing Date: 14 August 1998 (14.08.98)

(30) Priority Data:
2,209,804 15 August 1997 (15.08.97) CA(71) Applicant (for all designated States except US): POWER-
LASERS LTD. [CA/CA]; Advanced Technology Centre,
Units 2 & 3, 543 Mill Street, Kitchener, Ontario N2G 2Y5
(CA).

(72) Inventor; and

(75) Inventor/Applicant (for US only): GU, Hongping [CN/CA];
Apartment 127, 155 University Avenue West, Waterloo,
Ontario N2L 3E5 (CA).(74) Agents: ORANGE, John, R., S. et al.; Orange & As-
sociates, Toronto Dominion Bank Tower, Suite 3600,
Toronto-Dominion Centre, P.O. Box 190, Toronto, Ontario
M5K 1H6 (CA).(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR,
BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE,
GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ,
LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW,
MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL,
TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO
patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR,
IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published


With international search report.

Before the expiration of the time limit for amending the
claims and to be republished in the event of the receipt of
amendments.

(54) Title: METHOD OF LASER BEAM WELDING OF ZINC-COATED STEEL SHEET

(57) Abstract

A pair of coated components are laser welded to one another by initially forming protuberances on one of the components. The protuberances maintain juxtaposed surfaces separated and the components are then laser welded to one another. The separation of the surfaces vents vapor generated by the coating.



*(Referred to in PCT Gazette No. 15/2000, Section II)

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

METHOD OF LASER BEAM WELDING OF ZINC-COATED STEEL SHEET

The present invention relates to a method of making lap joint of zinc coated steel
5 sheets with a laser beam.

BACKGROUND OF THE INVENTION

The increased use of zinc-rich coated steel sheets in auto-body components for
enhanced corrosion resistance poses a demand for an acceptable welding method to join these
10 kinds of sheets. Laser beam welding has an advantage of low total heat input and thus causes
a low distortion to the zinc-rich coating on the sheet. Therefore laser beam welding is being
evaluated as a desirable joining technique for such sheet steel in butt and lap joint
configurations. However, a problem arises with welding these materials in the lap-joint
configuration due to the low boiling point of zinc (906°C) compared with the melting
15 temperature of steel (~1550°C).

If there is no joint clearance between the sheets the zinc vapor during welding can
only escape through the molten welding pool, and this typically results in excessive weld
porosity or complete expulsion of the weld metal. In order to make a good quality weld, there
are, in principle, two solutions to get around this problem: (1) creating a zinc-vapor venting
20 channel during welding; or (2) removing the zinc coating in the welding pass. Both of these
approaches need additional techniques to be realized. Many techniques have been developed
to provide a gap between sheets to perform laser welding and to remove the zinc coat at the
welding spot. These approaches typically require the use of supplementary components or
spacers and cannot be employed in the production line, since additional equipment is required
25 to create a gap or remove the coating. This will incur a significant expense and increase
production time.

It is therefore an object of the present invention to obviate or mitigate the above disadvantages.

SUMMARY OF THE INVENTION

5 The present invention is intended to provide a practical and flexible way of making laser beam lap weld of zinc coated steel sheets. In general terms, a laser beam interaction with one surface of the material is used to create an acceptable gap between the sheets before the welding pass is performed.

10 More specifically, protuberances are formed on one surface of one sheet by impingement of a laser beam which maintains opposed surfaces of the sheets in spaced relationship. In this manner, the welding may be completed entirely on a single welding apparatus in an efficient cost-effective manner. With such a technique, it is possible to make a curved welding pass and it is applicable to 3D welding configuration. Therefore, this technique makes the production of laser beam lap welds of the zinc coated steel sheets
15 possible using an existing butt welding system.

 The preferred embodiment of the invention relates to a method of creating a gap for vapor gas venting by the laser beam before welding is performed. The principle is that a laser beam pulse with an appropriate pulse length can melt a spot on the metal sheet when it interacts with the metal and solidification of the molten metal forms a protuberance. The
20 protuberance height above the sheet surface may be a few tenths millimeters. A series of protuberances in a line or curve serves as a spacer. When the laser pulse pre-processed sheet is put together with another sheet, a gap is formed. Laser welding can thus be performed along the spotted line/curve and go over the protuberances. The appropriate distance between two laser created protuberances depends upon the clamping force, laser beam power, scanning
25 speed and the thickness of the metal sheets. In lap welding, the sheet on which laser pulses

generate protuberances can be either the top one or the bottom one. For both configurations, good quality welds can be produced.

DESCRIPTION OF THE INVENTION

5 Embodiments of the invention will now be described by way of example only with reference to the accompanying drawings, in which

Figure 1 is a plan view of a pair of lap welded components;

Figure 2 is a view on the line 2-2 of the sequential steps in performing a weld on the components;

10 Figure 3 is an alternative embodiment showing the production of a spot weld;

Figure 4 is a photographic representation of a portion of one of the sheets shown in Figure 2;

Figure 5a is a photographic representation of a section on the weld shown in Figure 1;

15 Figure 5b is a photographic representation of a plan view of the weld shown in Figure 1; and

Figure 6 is photographic representations of welded components produced by the technique shown in Figure 2.

Referring therefore to Figure 1, a pair of components 10, 12 are connected by seam welding along a seam line 13 indicated in chain dot line. Each of the components is a steel sheet having oppositely directed surfaces 16, 17 and 18, 20 respectively. Each of the surfaces
20 has a rust inhibiting coating, typically a zinc coating 22 to provide protection from corrosion.

As shown in Figure 2, one of the components to be welded, namely zinc-coated steel sheet 10 is placed on a welding table (any kind of table used for laser welding). A series of laser beam pulses 14 transmitted through laser head 23 are used to impinge on one of the surfaces 16 of the sheet 10 to create a series of protuberances 15 along the intended weld line 13. This process can be done by moving laser beam 14 over the sheet 10 or by manipulating the focusing optics of the laser head.

Once the pulsed protuberances are formed, the zinc-coated steel sheet 12 is placed on top of the laser-pulsed sheet 10 so that surface 18 overlies the surface 16. Alternatively, of course, the laser-pulsed steel sheet 10 may be placed on top of the other zinc-coated steel sheet 12. Under either condition, the steel sheets 10, 12 are pressed together by a clamp (not shown). As a result, two sheets to be welded are held together and are ready to be welded.

The protuberances 15 form an air gap 24 between the opposed surfaces 16, 18 of overlapping portions of the zinc-coated steel sheets 10, 12 along the weld line 13.

The welding operation is carried out by applying laser beam 14 to the steel sheets 10, 12 as indicated in Figure 2 by arrow A. During the welding, the zinc vapor 26 of the zinc-coating 22 can flow into the air gap 24 surrounding the welding keyhole. Therefore, no air holes or very few air holes are formed in the solidified metal weld 19. Thus, the resultant weld is satisfactory in quality.

In a typical welding operation using a 1.5 kW CO₂ laser, the protuberances 15 were formed by beam pulses of 100 - 150 millisecond in duration. The thickness of the sheet 10 was ~1.0 mm and the material galvanized steel. The height of the protuberances 15 was in the order of 0.4 mm with a diameter of in the order of 2 mm. As can be seen from Figure 4, the protuberance is irregular but of sufficient height to maintain the surfaces 16, 18 separated. The spacing of the protuberances was about 50 mm for the material selected although this spacing may vary according to the material.

The components 10, 12 were seam welded using the 1.5 kW laser in continuous mode traveling at a welding speed of 1.5 in/sec. The resultant weld is shown in Figure 5 where it can be seen that good homogeneity has been obtained.

The above embodiment has been described with respect to seam welding but a similar
5 technique may be used for spot welding.

As shown in Figure 3, one of the components 10 to be welded is placed on a working table or frame. At the locations where laser spot welds are to be made, a laser beam pulse 14 impinges on surface 16 to create a protuberance 15. After all the locations are pulsed by laser beam 14, zinc-coated steel sheet 12 is placed on top and clamped. As a result of this
10 configuration, an air gap is formed between two zinc-coated steel sheets around the laser-generated humps. The welding operation is carried out by applying a laser beam 14 to the steel sheets adjacent to each protuberance 15. The laser beam draws a circle of small radius around the protuberance to provide a localized circular weld. Welding will not be affected if the path of the beam intercepts the protuberance.

15 As described in the seam welding embodiment above, the zinc vapor 26 escapes into the air gap around the hump. Therefore, a circular weld 19 is made and the resultant weld is satisfactory in quality. This circular weld can be considered as a spot weld.

It will be seen from the above description that the creation of natural spacer by this technique is simple and flexible as the laser beam can be put on anywhere on the sheet to
20 create protuberances and to perform welding. Moreover, implementation of lap welding can be done with present laser welding systems with little additional costs.

**THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE
PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:**

1. A method of laser welding a pair of juxtaposed components comprising the steps of
5 forming on one surface of one component a protuberance to project above said surface,
juxtaposing said components such that opposed surfaces are maintained separated by said
protuberance, and laser welding said components by impingement of a laser beam in the
region in which said surfaces are separated.
- 10 2. A method according to claim 1 wherein said protuberance is formed by impingement
by laser beam.
3. A method according to claim 1 wherein said weld is formed by rotating said beam
about one of said protuberance.
- 15 4. A method according to any preceding claim 1 in which a plurality to protuberances are
formed in spaced relationship along a surface of said one component.
5. A method according to claim 4 wherein said components are welded to one another by
20 translating said laser beam along said surface in the direction of said protuberances.
6. A method according to claim 4 wherein said components are welded to one another by
rotation of said beam about respective ones of said protuberances to provide a
generally circular weld.

25

7. A method according to any preceding claim wherein at least one of said components is coated with a rust inhibiting coating.

8. A method according to claim 7 wherein said coating includes zinc.

5

9. A method of welding a pair of sheet metal components having a corrosive resistant coating to one another comprising the steps of impinging a laser beam upon one surface of one of the components to form a plurality of localized protuberances thereon at spaced intervals, juxtaposing said sheets with said protuberances interposed between said sheets to maintain a separation thereof, and welding said sheets to one another by impingement of said beam in the vicinity of said protuberances.

10

10. A method according to claim 9 wherein said welding is performed by translating said beam across said components.

15

11. A method according to claim 10 wherein said beam is rotated about said protuberances to provide a circular weld.

12. A method according to claim 9 wherein said beam intersects said protuberances during welding.

20

1/6




Fig. 1




Fig. 2




Fig. 3




Figure 4

SUBSTITUTE SHEET (RULE 26)





Figure 5

SUBSTITUTE SHEET (RULE 26)

6/6




Figure 6

SUBSTITUTE SHEET (RULE 26)

INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 98/00779

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B23K26/00 B23K33/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B23K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	US 5 104 032 A (SPIES BERARD ET AL) 14 April 1992 see the whole document ---	1,4,5,7, 8 9,10
X A	FR 2 731 373 A (PEUGEOT) 13 September 1996 see the whole document ---	1,4,7,8 9
X A	US 5 454 480 A (MORRIS JR H EDWARD) 3 October 1995 see the whole document ---	1,4,7,8 9
X A	US 5 626 776 A (MORRIS JR H EDWARD) 6 May 1997 see the whole document ---	1,4,7,8 9
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

7 December 1998

Date of mailing of the international search report

17/12/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Aran, D

INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 98/00779

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 010, no. 130 (M-478), 14 May 1986 & JP 60 255294 A (KUBOTA TEKKO KK; OTHERS: 01), 16 December 1985	1,7,8
A	see abstract ---	9
X	DE 38 12 448 C (BAYERISCHEN MOTORENWERKE AG) 15 June 1989	1,7,8
A	see the whole document ---	9,10,12
A	US 5 389 761 A (KRESSE JR ALFRED L) 14 February 1995 see the whole document -----	1,9

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/CA 98/00779

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5104032	A	14-04-1992	DE 3933408 A EP 0421091 A ES 2048374 T JP 2571976 B JP 3193285 A	30-08-1990 10-04-1991 16-03-1994 16-01-1997 23-08-1991
FR 2731373	A	13-09-1996	NONE	
US 5454480	A	03-10-1995	US 5626776 A	06-05-1997
US 5626776	A	06-05-1997	US 5454480 A	03-10-1995
DE 3812448	C	15-06-1989	EP 0337182 A	18-10-1989
US 5389761	A	14-02-1995	DE 4432912 A	30-03-1995

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

